

## C2ET Rigid Quality Cement Based Tile Adhesive

### DESCRIPTION

**ACT ADH-22** is a rigid, quality, cement based tile adhesive used for internal and external wall & floor applications including swimming pools. Recommended for tiling over concrete, sand and cement screeds, rendered block and brick work. **ACT ADH-22** can be mixed with **ACT AD-1** to produce a flexible and improved adhesion strength adhesive. **ADH-22** is suitable for internal and external applications including, bathrooms, laundries, toilets, kitchens, decks and patios. **ACT ADH-22** is suitable for adhering ceramic tiles such as bicottura, monocottura, natural stone and mosaic tiles.

### FEATURES & BENEFITS

- ◇ **C2** - High Adhesion Strength
- ◇ **E** - Extended Open Time
- ◇ **T** - Non Slip/Non Slump
- ◇ Infused Primer Technology (**IP**T)

### SUITABLE FOR

- ◇ Concrete
- ◇ Sand & cement screeds
- ◇ Rendered Block & Brickwork
- ◇ Swimming Pools (mixed with **AD-1**)
- ◇ Areas covered under AS3958.1-2007

### PERFORMANCE DATA

Exceeds the performance requirements of AS4992  
 Tensile adhesive strength  $\leq 1.0$ MPa (28 days)

### COVERAGE

20kg bag will cover 5m<sup>2</sup> with 10mm notch trowel.

### SUBSTRATE PREPARATION

All substrates to be tiled over must be clean, dry, free from dust, wax, oil, grease, laitance, curing compounds, paints (inc overspray) coatings and all contaminants which may cause adhesion failure. Concrete must be cured for 28 days. Sand and cement screeds and renders must be cured for 7 days. If in doubt with any of above please contact **ACT Australia Technical Services**.

### PRIMING

In normal circumstances no priming is required as **ACT ADH-22** has unique Infused Primer Technology (**IP**T). To test substrate sponge liberal amounts of water onto the substrate and ensure water absorption is taking place. If so, then only sponge down with clean water prior to spreading adhesive. If water is beading or no absorption is taking place then prime with **ACT PR-1** impervious primer.

### MIXING

20kg of **ACT ADH-22** powder will require approximately 5 litres of clean drinking water. Slowly add **ADH-22** powder into a clean bucket with the measured water. Slowly mix with a quality drill & mixing paddle to ensure a smooth, lump free tooth paste consistency. Leave the mix for 3 minutes then re-stir. The adhesive is now ready for use.

### MOVEMENT JOINTS

Movement joints must be incorporated within the tiling system in accordance with AS3958.1-2007. Ensure movement joints are free of all adhesive and grout residue.

### APPLICATION

All workmanship must be in accordance with AS3958.1-2007. After mixing adhesive, apply the adhesive with the appropriate size notch trowel for the application. Ensure to work the adhesive to the substrate for good adhesion. Adhesive should sit up and not slump whilst being wet and tacky prior to laying tiles. Open time is approximately 30 mins at 23°C. If the adhesive has skinned over prior to laying tiles then remove and apply fresh adhesive. Ensure minimum adhesive bed thickness is 2mm for wall & 4mm for floor applications depending on size of tile.

### DRYING

Allow minimum 24hrs for the adhesive to cure and set prior to grouting. Lower temperatures will delay curing. If temperature is below 5°C or above 35°C. do not tile. For continuous water immersion, allow minimum 7 days. Ensure adhesive has set prior to grouting.

### GROUTING

Use **ACT Australia** recommended grouts. Ensure grout joints are clean of any adhesives residue prior to mixing grout with clean water to a toothpaste consistency.

### SHELF LIFE

In unopened original packaging for up to 12mths when stored in a cool, dry environment off the floor.

### SAFETY DIRECTIONS

**ACT Australia** supports best practise in material handling. Appropriate gloves, dust masks, safety glasses and protective clothing should be worn. If product comes in contact with skin, wash off with soapy water. Avoid inhaling dust by wearing appropriate dust mask. If swallowed, drink plenty of drinkable water and seek medical advice. In case of contact with the eyes, rinse with clean water or eye wash solution and seek medical advice.

### LIMITATIONS

- ◇ Not suitable for tiling directly over 100% polyurethane or fibreglass waterproofing membranes.
- ◇ Not suitable for tiling directly over plastics and metals.
- ◇ Not suitable for tiling directly over Masonite, MDF, timber, plywood or particleboard.
- ◇ Not suitable for moisture sensitive stone such as green marble or manmade conglomerate products.
- ◇ External tiling should not exceed 2.7m in height.
- ◇ Suspended concrete slabs must conform to AS3958.1-2007 for maximum deflection. All post-tensioned concrete slabs must be treated as flexible substrate.
- ◇ If in doubt, contact **ACT Australia Technical Services** for further information and advice.